

TQC PERMEABILITY CUPS

VF2200, VF2201

MANUAL

1 PRODUCT DESCRIPTION

Permeability cups for determining the water-vapor transmission of paints, varnishes, coatings, coating systems and related products. The Permeability cup consists of a cup, seal ring and cover ring. The seal ring is designed to prevent turning when closing the cover. The Permeability cup is suitable for testing both self-supporting coating and non-self-supporting coatings. Water-vapor transmission is of interest for high humidity conditions. The wet cup method is thus the reference method for determining water-vapor transmission, if agreed upon otherwise, other procedures or conditions the dry cup method may be used.

**1.1 Specifications**

Article number	VF2200	VF2201
Surface area:	10 cm ²	25 cm ²
Internal diameter:	35,7	56,40
External diameter:	65,8	89,0
Mass: (of empty cup)	Approx. 70 g.	Approx. 94,2
Material:	Anodized Aluminium	Anodized Aluminium

2 STANDARDS

ISO 7783 (supersedes NF T30-018), ASTM D1653, ASTM E95

3 WHAT'S IN THE BOX?

Permeability cup, consists of:

- Cup
- Seal ring
- Cover ring

4 PREPARATIONS

When using the Permeability cup take care that all surfaces are clean and smooth. Any deformation to the Permeability cup can cause deviation in the obtained result.

5 PERFORM A MEASUREMENT

Taking a reading:

The Permeability cup can be used in both a wet-cup and dry-cup method. Due to the reference method of the wet cup method, only this method will be described. For execution of the dry cup method see the appropriate standard

- 1 Prepare the film (coating material) to be tested, either in self-supporting or non-self-supporting form.
 - a. Self-supporting coating films can best be created using a non-stick substrate, for example silicone coated paper. The suitable non-stick substrate can vary per application.
 - b. The sample can be cut to the appropriate size by using the seal ring as a cutting guide.



- 2 Fill the Permeability cup with the specified volume or to the specified distance from the edge with the required liquid or for the dry cup method with dry desiccant.



- 3 Place the pre-cut sample over the seal ring and align.
- 4 Place the seal ring with the sample on the flange of the cup, such that the film is between the cup flange and the seal ring. Make sure that the seal ring is properly aligned to the pins on the outside of the flange.



- 5 Place the sealing ring and screw hand tight.



- 6 Weigh the assembly and record the mass in grams (M_1) by means of a balance suitable to determine the change in mass of the test assembly. Balances with a resolution of 0,001g are found the most suitable.



- 7 Place the cup in a test environment as stated in the standard and leave it undisturbed for the period of time stated in the test protocol/standard.
- 8 Weigh the assembly and note the weight at regular intervals (M2) until the mass loss per hour is linear.
- 9 Calculate the water-vapour transmission rate of the film in grams per square metre per day (g/(m²/d)). The required formula for the calculation depends on the used method dry cup or wet cup.
- 10 In order to open and clean the cup after the test the seal ring can best be released using the openings on the side of the cup.



- 9 After testing always store the clean cup in a dry environment.

6 MAINTENANCE

- Always clean the instrument after use with a suitable solvent.
- Never clean the instrument by mechanical means such as a wire brush or abrasive paper. This may cause like the use of aggressive cleaning agents permanent damage.
- Regularly check the instrument for defects.

7 DISCLAIMER

The right of technical modifications is reserved.

The information given in this manual is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this manual without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Whilst we endeavour to ensure that all advice we give about the product (whether in this manual or otherwise) is correct we have no control over either the quality or condition of the product or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this manual is liable to modification from time to time in the light of experience and our policy of continuous product development.